

HOT JOINT PAINT

GENERAL INFORMATION

BS EN 12591 Paving Grade 40/60 Bitumen

Primarily used for sealing edges of freshly laid tarmac.

Black and semi-solid in appearance. Can be supplied in 12.5 KG containers, 20 KG plastic buckets and 20KG tins.

Contents of containers should be removed and put into a bitumen boiler. It is important to ensure that containers and application area is free of water to avoid instant steam formation from molten bitumen

Recommended heating temperature of 150°C

CHARACTERISTICS

Property	Units	Test Method	Specified Limit(s)
Penetration at 25°C	dmm	EN1426	40-60
Softening Point	°C	EN1427	≥ 50
Flash Point (COC)	°C	-	215
Density	-	-	approx 1