



Buff Grey Multi Technical Data Sheet

CED Stone Group
 728 London Road, Grays,
 Essex RM20 3LU
 technical@cedstone.co.uk
 estimators@cedstone.co.uk
 sales@cedstone.co.uk
 01708 867 238
 www.cedstone.co.uk
 Company Reg. No. 624843

Product Code:
 S35-105-2817

Stone Classification
 Sandstone

Source
 Yorkshire-England



Please note:

Sawn tonality variation and finish; Natural variations may occur between image and finished product.



Project Shot:

Sawn Buff Multi Yorkstone Paving



Test	Value	BS EN
Apparent density (g/cm ³)	2.44	1936: 2006
Water Absorption (%)	2.19	13755: 2008
Abrasion Resistance (mm)	18	14157: 2017
Flexural Strength (Mpa) LEV	10.2	12372: 2006
Flexural Strength (Mpa) Mean	12	12372: 2006
Flexural freeze thaw (Before/After)	8.7/9.6	12371: 2010
Compressive Strength (Mpa) LEV	94	1926: 2006
Compressive Strength (Mpa) Mean	118	1926: 2006
Compressive freeze thaw (Before / After)	94/108	12371: 2010
Slip Resistance Sawn Dry/Wet	95/83	14231: 2003

British Standards:

Paving, Setts and Kerbs are CE marked to BS EN 1341, 1342 and 1343.

Tolerances:

Stone dimensions are produced to meet class 1 specification as a minimum.

Quality Control:

Stone supplied in accordance with ISO 9001 quality standards.

Maintenance:

Clean warm water with natural soap would be the most common method of cleaning the stone.

We also offer a wide range specialist cleaning products and impregnators. Please contact our technical department for any further information.

Inspiring beautiful landscapes