

Classic Buff Technical Data Sheet

Product Code:
S35-22141-B

Stone Classification
Sandstone

Source
Yorkshire-England  **Date Created:** 16/12/21



Please note:

Sawn tonality variation and finish; Natural variations may occur between image and finished product.



Project Shot:

Sawn textured Classic Buff Yorstone paving.



Test	Value	BS EN
Apparent density (g/cm ³)	2.38	1936: 2006
Water Absorption (%)	2.7	13755: 2008
Abrasion Resistance (mm)	18.5	14157: 2017
Flexural Strength (Mpa) LEV	11.6	12372: 2006
Flexural Strength (Mpa) Mean	13.9	12372: 2006
Compressive Strength (Mpa) LEV	87	1926: 2006
Compressive Strength (Mpa) Mean	104	1926: 2006
Freeze thaw: Before / After (Mpa)	13.9/14.2	12371: 2010
Slip Resistance Sawn Dry/Wet	86/70	14231: 2003
Open Porosity (%)	8.3	1936: 2006

British Standards:

Paving, Setts and Kerbs are CE marked to BS EN 1341, 1342 and 1343.

Tolerances:

Stone dimensions are produced to meet class 1 specification as a minimum.

Quality Control:

Stone supplied in accordance with ISO 9001 quality standards.

Maintenance:

Clean warm water with natural soap would be the most common method of cleaning the stone.

We also offer a wide range specialist cleaning products and impregnators. Please contact our technical department for any further information.

Inspiring beautiful landscapes