


Product Code:
S215-2712-2094


Stone Classification
Gabbro/Dolerite

Source
Scotland 

Date Created: 24/07/20



Please note:

Image shows Flame Textured tonality variation and finish; Natural variations may occur between image and finished product. 

Project Shot:

Flame textured Scottish Whin Paving, Steps and Copings



Test	Value	BS EN
Apparent density (g/cm ³)	2.91	1936: 2006
Water Absorption (%)	0.3	13755: 2008
Abrasion Resistance (mm)	17	14157: 2017
Flexural Strength (Mpa) LEV	25	12372: 2006
Flexural Strength (Mpa) Mean	26.5	12372: 2006
Compressive Strength (Mpa) Mean	209	1926: 2006
Freeze thaw: Before / After (Mpa)	23.9/22.9	12371: 2010
Slip Resistance Flame Textured Wet	74	12371: 2010
Slip Resistance Bush Hammered Wet	77	14231: 2003
Open Porosity (%)	0.7	1936: 2006
PPV Flame Textured/Bush Hammered	58/65	7932: 2003

British Standards:

Paving, Setts and Kerbs are CE marked to BS EN 1341, 1342 and 1343.

Tolerances:

Stone dimensions are produced to meet class 1 specification as a minimum.

Quality Control:

Stone supplied in accordance with ISO 9001 quality standards.

Maintenance:

Clean warm water with natural soap would be the most common method of cleaning the stone.

We also offer a wide range specialist cleaning products and impregnators. Please contact our technical department for any further information.

Inspiring beautiful landscapes