

MACTEX[®] H1000

NEEDLEPUNCHED & THERMOCALENDERED NONWOVEN GEOTEXTILES

MACTEX[®] H are nonwoven geotextiles manufactured with virgin high tenacity polypropylene fibers assembled by a needlepunched treatment and thermocalendered. The fabrics are CE marked according to EN 13249, 13250, 13251, 13252, 13253, 13254, 13255, 13256, 13257, 13265 for the following intended uses: F, D, R, F+D, F+S+D, F+R+S, F+S, R+S, F+R.

MACTEX[®] H

			1000	
Mechanical and Hydraulic properties				
Tensile strength (MD)	EN ISO 10319	kN/m	8	1,2
Tolerance			-0.8	
Strain at max load (MD)	EN ISO 10319	%	55	1
Tolerance			-11	
Tensile strength (CD)	EN ISO 10319	kN/m	9	1,2
Tolerance			-0.9	
Strain at max load (CD)	EN ISO 10319	%	60	1
Tolerance			-12	
Static Puncture Resistance - CBR	EN ISO 12236	N	1.500	1
Tolerance			-250	
Dynamic Puncture Resistance - Cone Drop	EN ISO 13433	mm	35.0	1
Tolerance			+3.5	
Permeability - normal to plane	EN ISO 11058	l/m ² sec	110	1,3
Tolerance			-33	
Opening Pore Size O ₉₀	EN ISO 12956	µm	95	1
Tolerance			± 28.5	
Physical properties - typical				
Warp and Weft Polymers			Polypropylene	
Mass per unit	EN ISO 9864	g/m ²	110	1
Roll width		m	5.85	4
Roll length		m	150	4



NOTE:

- 1: Mean value; if not differently indicated a standard 10% tolerance value is admitted;
- 2: T_{ch} corresponds to the mean value deducted the tolerance and corresponds to the MARV at 95% of confidence limit;
- 3: The Constant Head Permittivity Test was performed at 50mm.
- 4: Nominal value; a standard 1% tolerance is admitted.

MD : longitudinal direction
 CMD : transversal direction

For the optimisation and improvement process of the technical characteristics of the products, the producer reserves the factibility to modify standard and characteristics at the product without any warning. The information contained herein is to the best of our knowledge accurate, but since the circumstances and conditions in which it may be used are beyond our control, we do not accept any liability for any loss or damage, however arising, which results directly or indirectly from the use of such information nor do we offer any warranty or immunity against patent infringement.

© Maccaferri Ltd. All rights reserved. Maccaferri will enforce Copyright.